



UL VERIFICATION SERVICES INC.

SOFTLINES TESTING LABORATORY • 2601 SE OTIS CORLEY DRIVE • BENTONVILLE, AR 72712
PHONE: (479) 286-2300 • FAX: (479) 286-2301 • BEN.Softlines.Customer.Service@crs.ul.com

Evaluation of Test Results

Lab Report No: ARSL2800024

Issue Date: August 29, 2023

Item Description: Jla Ii-Imani Comforter Set



Rating: **Pass**

CLIENT: E&E Co Ltd

BUYER: Supplier Testing

DEPARTMENT: Not Applicable

BRAND: Not Private Label (National)

ORDER TYPE: Domestic

SOURCING OFFICE: Not Applicable

TEST TYPE: Supplier Only-Full Testing

VENDOR STOCK NUMBER: II10-1089

REASON FOR TESTING: evaluation of appearance, fiber, weight, thread count, measurement, and durability

COUNTRY OF ORIGIN: India

SUPPLIER NAME: E&E Co Ltd

HOST VENDOR NUMBER: 444096

SUPPLIER ID: 28009219

FACTORY NAME: Not Applicable

FACTORY NUMBER: Not Applicable

CHILDREN'S PRODUCT: No

*** Please see the following pages for additional item information ***

This letter / report / certificate shall not be reproduced (except in full version) without the written approval of the UL Company. ("UL")

LETTERS / REPORTS / CERTIFICATES: Letters / Reports / Certificates of UL are issued for the exclusive use of the Customer to whom they are addressed. No quotation from reports / certificates or use of the UL's name is permitted except by UL's express written authorization. Letters / reports / certificates apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. Reports / Certificates of UL do not relieve sellers / suppliers from their contractual responsibilities with regard to the quality / quantity of the goods in delivery nor do they prejudice the Customer's right to claim against sellers / suppliers for compensation for any apparent and/or hidden defects not detected during UL's random inspection or testing or audit. The liability of UL to the Customer in contract, tort (including negligence or breach of statutory duty) or howsoever, and whatever the cause thereof, (a) for any loss of profit, business, contracts, revenues, or anticipating savings; or (b) for any special indirect or consequential damage of any nature whatsoever, shall be limited to the amount of the fee paid in respect of the specific Work(s) which give rise to such claim.

For Reports / Certificates, refer to the UL VS Terms and Conditions.

Decision Rule: the declaration of conformity is given not taking into account the measurement uncertainty.

Level of risk associated with the Decision Rule: The results issue by UL Solutions does not take in consideration the measurement uncertainty, but when the value is close to the limit, the test, if repeated by another laboratory,

ADDITIONAL SAMPLE INFORMATION

SIZE(S)	COLOR(S)
Full/Queen	Grey
PO NUMBER(S)	
Not Applicable	
UPC CODE(S)	
Not Applicable	
ITEM NUMBER(S)	
Not Applicable	
APPLICATION ID	FABRIC CONSTRUCTION
6099462	Woven

UL VERIFICATION SERVICES INC.



Abdel Rodriguez
LABORATORY LEAD

UL VERIFICATION SERVICES INC.



Dawnell Smith
LABORATORY MANAGER

This letter / report / certificate shall not be reproduced (except in full version) without the written approval of the UL Company. ("UL")

LETTERS / REPORTS / CERTIFICATES: Letters / Reports / Certificates of UL are issued for the exclusive use of the Customer to whom they are addressed. No quotation from reports / certificates or use of the UL's name is permitted except by UL's express written authorization. Letters / reports / certificates apply only to the specific materials, products or processes tested, examined or surveyed and are not necessarily indicative of the qualities of apparently identical or similar materials, products or processes. Reports / Certificates of UL do not relieve sellers / suppliers from their contractual responsibilities with regard to the quality / quantity of the goods in delivery nor do they prejudice the Customer's right to claim against sellers / suppliers for compensation for any apparent and/or hidden defects not detected during UL's random inspection or testing or audit. The liability of UL to the Customer in contract, tort (including negligence or breach of statutory duty) or howsoever, and whatever the cause thereof, (a) for any loss of profit, business, contracts, revenues, or anticipating savings; or (b) for any special indirect or consequential damage of any nature whatsoever, shall be limited to the amount of the fee paid in respect of the specific Work(s) which give rise to such claim.

For Reports / Certificates, refer to the UL VS Terms and Conditions.

Decision Rule: the declaration of conformity is given not taking into account the measurement uncertainty.
Level of risk associated with the Decision Rule: The results issue by UL Solutions does not take in consideration the measurement uncertainty, but when the value is close to the limit, the test, if repeated by another laboratory,



UNDER PENALTY OF LAW
 THIS TAG NOT TO BE REMOVED
 EXCEPT BY THE CONSUMER

ALL NEW MATERIAL
 100% Consisting of
 POLYESTER FIBER
 REG. NO. UT2619(IN)

Certification is made by the manufacturer
 that the materials in this article are
 described in accordance with law

MADE FOR
 E&E CO., LTD.
 45875 Northport Loop East
 Fremont, CA 94538

Date of Delivery: _____
 Finished Size: 88 in x 92 in (224 cm x 234 cm)
 Net Weight of Filling Material: 2 lb 14 oz (1.30 kg)
 Cover: Face: 100% Cotton
 Reverse: 100% Cotton
 Federal RN # 91519

MADE IN INDIA

Face:
 100% Cotton

Reverse:
 100% Cotton

Filling:
 100% Polyester

Machine wash cold,
 gently and separately.
 Do not bleach. Tumble dry Low.
 If there is no free movement in
 washer or dryer, use large capacity
 commercial machine.
 Remove promptly. Do not iron.

Made in India
 RN 91519



LABELING		
	RATING	COMMENTS
Country of origin (required by FTC or U.S. Customs Regulations 19 CFR Part 134 if imported)	P	
Manufacturer's Identification (required by FTC or Customs) Date Code: _____ --- _____	P	
Fiber content (required by FTC)	P	
Care instructions Written / Symbols (as defined in ASTM 3136 / ASTM D 5489)	P	
LABELED CARE INSTRUCTIONS:		
<i>Machine wash cold gently and separately. Do not bleach. Tumble dry low. If there is no free movement in washer or dryer, use large capacity commercial machine. Remove promptly. Do not iron.</i>		

GENERAL APPEARANCE, WORKMANSHIP / CONSTRUCTION

	RATING	COMMENTS
<u>Construction / Workmanship</u> Seams are neat with no loose threads, needle damage, open seams	P	
Hems are straight, uniform, and consistent	P	
Loose threads are properly trimmed	P	
<u>Fabric Defects</u> No major defects, such as holes, runs, snags, stains, slub yarns, etc., or any other irregularities as defined in ASTM D3990	P	
<u>Evenness of Color</u> Uniform and even color within the sample and between samples	P	
<u>Measurements</u> All measurements conform to labeled dimensions	P	

APPEARANCE / DURABILITY AFTER LAUNDERING OR DRYCLEANING

	RATING	COMMENTS
<u>General Appearance after Laundering</u> No open seams, holes, snags, runs, loose threads, excessive pilling, puckering, etc.	P	
<u>Shape Distortion after Laundering</u> No evidence of twisting	P	
<u>Durability Seam / Hem after Laundering</u> No open seams or broken stitches	P	
<u>Batting / Stuffing Durability & Cleanliness</u> No disintegration or noticeable migration (lumpiness) after laundering	P	
Loose fillers are free of objectionable matter and contamination such as animal infestation, splinters, metal chips, etc.	P	

FIBER CONTENT Method References: AATCC 20, AATCC 20A, ASTM D629					
Sample Material Evaluated	%	Labeled Fiber Content	%	Actual Fiber Content	RATING
Comforter Shell - Grey - Woven	100%	Cotton	100%	<i>Cotton</i>	P
Fill	100%	Polyester	100%	<i>Polyester</i>	P

COLORFASTNESS			
TEST CONDUCTED	RESULT	REQUIREMENT	RATING
LAUNDERING - AATCC 135/150 (3 cycles) Gray Scales for Color Change / Staining Comforter/Sham- Grey/Charcoal/White - 1			
<i>SHADE CHANGE GRADE:</i>	4.0	≥ 4.0	P
Comforter/Sham- Grey - 2			
<i>SHADE CHANGE GRADE:</i>	4.5	≥ 4.0	P
COLORFASTNESS TO CROCKING - AATCC 8 Comforter/Sham- Grey/Charcoal/White - 1			
<i>DRY CROCKING GRADE:</i>	4.5	≥ 4.0	P
<i>WET CROCKING GRADE:</i>	3.0	≥ 3.0	P
Comforter/Sham- Grey - 2			
<i>DRY CROCKING GRADE:</i>	4.5	≥ 4.0	P
<i>WET CROCKING GRADE:</i>	4.5	≥ 3.0	P

FABRIC WEIGHT

TEST CONDUCTED	Actual Weight (oz/yd ²)	Actual Weight (g/m ²)	Specified Weight oz/yd ² (single value or range)	Specified Weight g/m ² (single value or range)	RATING
<i>FABRIC WEIGHT - ASTM D 3776 meets specified weight or weight range</i>					
Comforter Front - Grey	4.10	139.01	---	---	---
Comforter Fill	7.32	248.19	---	---	---
Comforter Back - Grey	4.05	137.32	---	---	---
Shams Front - Grey	4.15	140.71	---	---	---
Shams Lining	0.58	19.67	---	---	---
Shams Back - Grey	3.97	134.61	---	---	---

DIMENSIONAL STABILITY

TEST CONDUCTED	Original Size (in.)	Size After Washing (in.)	Shrinkage / Growth	Requirement	RATING
<i>DIMENSIONAL STABILITY (WASHING) - AATCC 135 / 150</i> (-) denotes shrinkage Comforter - Grey					
Face					
Length	18.00	17.50	-2.8%	≤ 3.5%	P
Width	18.00	17.50	-2.8%	≤ 3.5%	P
Back					
Length	18.00	17.50	-2.8%	≤ 3.5%	P
Width	18.00	17.50	-2.8%	≤ 3.5%	P
Sham - Grey					
Face					
Length	18.00	17.38	-3.4%	≤ 3.5%	P
Width	10.00	9.75	-2.5%	≤ 3.5%	P
Back					
Length	10.00	9.75	-2.5%	≤ 3.5%	P
Width	10.00	9.75	-2.5%	≤ 3.5%	P
<i>Shrinkage is indicated with a "-"; Growth is indicated with a "+"</i>					

MEASUREMENT - BED COMFORTER (TOP OF BED)						
#1		COLOR: <u>Comforter - Grey</u>			SIZE: <u>Full/Queen</u>	
Tolerance (in.) - +	Component Description	Measurement Location	Labeled (in.)	Actual Flat / Circ. (in.)	Difference + / - (in.)	RATING
-2 3	Bed Comforter - Top of Bed	<i>Length</i>	92.000	95.000	3.000	P
-2 3	Bed Comforter - Top of Bed	<i>Width</i>	88.000	91.000	3.000	P
MEASUREMENT - PILLOW SHAM (TOP OF BED)						
#1		COLOR: <u>Sham - Grey</u>			SIZE: <u>Full/Queen</u>	
Tolerance (in.) - +	Component Description	Measurement Location	Labeled (in.)	Actual Flat / Circ. (in.)	Difference + / - (in.)	RATING
-0.5 1	Pillow Sham - Top of Bed	<i>Length</i>	---	26.125	---	---
-0.5 1	Pillow Sham - Top of Bed	<i>Width</i>	---	19.875	---	---